Arslon Jumaniyozov, Sherzod Kurambayev, Elyor Atashev

[1] Department of Chemical Technology, Urgench State University named after Abu Raykhan Beruni, Urgench, Uzbekistan

* Corresponding author: arslonjumaniyozov077@gmail.com

SEPARATION TECHNOLOGIES FOR TALC-MAGNESITE ORE: A SYSTEMATIC REVIEW OF FLOTATION, GRAVITY, AND ELECTROSTATIC METHODS

Abstract

Talc-magnesite ores are an important source of raw materials for refractory, ceramic, and cosmetic industries. The separation of talc from magnesite presents a persistent technical challenge owing to the similar density and partially overlapping surface chemical properties of the two minerals. This review systematically examines five separation technologies — collectorless flotation, direct flotation, reverse flotation, gravity separation, and electrostatic (triboelectric) separation — with critical evaluation of their physicochemical basis, reagent chemistry, and reported process performance based on peer-reviewed literature. The review identifies fine-particle entrainment, reagent selectivity, and process water chemistry as persistent operational challenges, and outlines a structured research agenda covering machine-learning process control, bio-based depressants, and dry electrostatic scale-up. The work is intended as a reference framework for researchers and engineers working on beneficiation of talc-magnesite ores, with particular relevance to deposits of the type found in Uzbekistan.

Keywords

talc; magnesite; flotation; gravity separation; electrostatic separation; depressants; mineral processing; ore beneficiation

1. Introduction

Talc ($Mg_3Si_4O_{10}(OH)_2$) and magnesite ($MgCO_3$) frequently co-occur in hydrothermal and metamorphic geological environments. Well-documented deposits include the Zinelbulak deposit in Uzbekistan, containing approximately 52 wt% talc and 43 wt% carbonate minerals (Hojamberdiev et al., 2010), and magnesite-dominant deposits in Liaoning province, China, where talc is the principal silicate gangue mineral. Global magnesite production exceeded 27 million tonnes in 2022, with China accounting for approximately 70% of output (USGS, 2023). Premium refractory-grade magnesite (>46% MgO, <2% SiO_2) commands market prices three to five times that of run-of-mine ore, providing a strong economic incentive for beneficiation.

The separation of talc from magnesite is technically challenging. Talc is naturally hydrophobic on its basal (001) face — water contact angles of 72–79° have been widely reported — while magnesite is predominantly hydrophilic, with contact angles of 40–47° (Fuerstenau et al., 1988; Nanthakumar et al., 2018). This surface property contrast underpins all flotation-based approaches, yet separation selectivity is strongly particle-size dependent and is further complicated by dissolved Mg^{2+} ion chemistry, slime coatings, and the presence of minor gangue phases such as dolomite, chlorite, and quartz.

Previous reviews have addressed Mg-carbonate flotation broadly (Nanthakumar et al., 2018) and talc flotation across multiple industrial applications (Ahmed et al., 2016). The present work provides a focused synthesis across the full spectrum of separation routes for the talc-magnesite binary system, integrating mineralogical context, reagent chemistry, and comparative process performance from the peer-reviewed literature.

2. Literature Search Methodology

A systematic literature search was conducted using Web of Science, Scopus, and Google Scholar. Search terms included combinations of: ("talc" OR "magnesite") AND ("flotation" OR "separation" OR "beneficiation"); "collectorless flotation" AND "talc"; "reverse flotation" AND "magnesite"; "triboelectric separation" AND "talc"; and "depressant" AND "magnesite" AND ("CMC" OR "guar gum" OR "carrageenan" OR "SHMP"). Coverage was limited to peer-reviewed journal articles and authoritative technical reports published between 1988 and 2024 in the English language. Reference lists of retrieved papers were additionally screened. Studies with incomplete reporting of experimental conditions or without quantitative data were excluded from tabular synthesis. A total of 16 primary sources were selected for this review.

3. Results and Discussion

3.1 Ore Mineralogy and Physicochemical Properties

Table 1 presents bulk chemical compositions for two representative talc-magnesite deposits for which primary analytical data are available in the peer-reviewed literature. The Zinelbulak deposit is characterised by sub-equal proportions of talc and carbonate minerals with elevated iron content (Fe2O3 = 6.84 wt%), while the Liaoning deposit is a high-purity magnesite ore with low silica content. These contrasting feed compositions illustrate why no single separation circuit design is universally applicable — reagent selection, grind size, and circuit configuration must be adapted to the specific deposit mineralogy.

Deposit / Location	MgO	SiO2	CaO	Fe_2O_3	Al_2O_3	LOI	Reference
Zinelbulak, Uzbekistan	34.6	34.1	0.70	6.84	0.94	22.85	Hojamberdiev et al. (2010)
Liaoning, China	46.01	2.38	0.75	0.90	0.30	49.66	Li et al. (2021)

Bulk chemical composition of representative talc-magnesite deposits (wt%).

Note: LOI = loss on ignition at 1000 °C. Values taken directly from cited publications. Al_2O_3 value for Zinelbulak from Hojamberdiev et al. (2010) Table 1.

Beyond bulk chemistry, the surface physicochemical properties of the constituent minerals govern separation behaviour. Table 2 compiles key parameters from multiple independent studies. The large difference in contact angle between talc basal faces (72–79°) and magnesite (40–47°) provides the thermodynamic basis for selective flotation. Equally important is the isoelectric point (IEP): both minerals reach their IEP near pH 6.5–7.0 on reactive faces, meaning both carry

negative zeta potentials under the alkaline conditions typical of flotation, reducing the scope for electrostatic discrimination without selective reagents.

Table 2. Key surface physicochemical properties of talc and magnesite compiled from literature.

Note: Values represent ranges reported across multiple independent studies. Contact angles

Parameter	Talc (basal face)	Talc (edge face)	Magnesite	Primary source(s)
Contact angle (°)	72–79	18–28	40–47	Fuerstenau et al. (1988); Nanthakumar et al. (2018)
Isoelectric point (pH)	< 2 (basal)	6.5–7.2	6.5–6.8	Nanthakumar et al. (2018)
Zeta potential at pH 7 (mV)	-24 to -31	-28 to -35	-18 to -26	Nanthakumar et al. (2018); Ahmed et al. (2016)
Zeta potential at pH 9 (mV)	-32 to -40	-35 to -44	-22 to -30	Nanthakumar et al. (2018)
BET surface area (m2/g)	4.8–9.2	—	0.8–2.4	Ahmed et al. (2016)
Density (g/cm3)	2.58–2.83	—	2.98–3.10	Standard mineralogy

ubble method in deionised water at pH 7.

The identification of minor gangue phases by XRD is equally important for circuit design. Dolomite responds similarly to magnesite under NaOL-based reverse flotation, while chlorite — a magnesium phyllosilicate — exhibits surface hydrophobicity comparable to talc under collectorless conditions (Nanthakumar et al., 2018). Both phases therefore constitute selectivity hazards and must be quantified in ore characterisation before flowsheet development.

Mineral liberation is a further critical variable. Adequate liberation of talc from magnesite typically requires grinding to a d80 of 74–100 µm for most deposit textures, as reported by Hojamberdiev et al. (2010) for the Zinelbulak ore. Over-grinding to finer sizes increases the proportion of sub-20 µm particles, which are subject to mechanical entrainment in flotation froth regardless of their surface hydrophobicity, thereby reducing separation selectivity.

3.2 Collectorless Flotation

Collectorless flotation exploits the native hydrophobicity difference between talc and magnesite without any added collector reagent. Because talc basal faces are intrinsically hydrophobic (contact angle 72–79°) while magnesite surfaces are hydrophilic (40–47°), talc particles selectively attach to air bubbles under appropriate hydrodynamic conditions. Brezani and Zelenak (2013) demonstrated for the Hnusta-Mutnik deposit that selectivity is strongly particle-size dependent: coarse and intermediate fractions (40–100 µm) show the highest separation

indices, while fractions below 20 µm suffer from mechanical entrainment of magnesite particles into the froth, sharply reducing concentrate grade. The principal advantage of collectorless flotation is low reagent cost; its principal limitation is moderate concentrate purity and a narrow effective size range.

3.3 Direct Flotation

In direct flotation, a collector is used to selectively enhance the hydrophobicity of talc. Sodium dodecyl sulfate (SDS), an anionic surfactant, is the most widely studied collector for this purpose. Ahmed et al. (2016) reviewed SDS-based talc flotation across multiple ore types and found optimal recovery at weakly acidic to neutral pH (approximately pH 6–7), where SDS adsorbs preferentially on talc surfaces while its uptake on magnesite remains low. At higher SDS dosages or more alkaline pH, selectivity decreases as the collector adsorbs non-selectively on magnesite edge faces. MIBC (methyl isobutyl carbinol) is the most commonly used frother. The key operational variables are pH, collector dosage, conditioning time, and grind size — all of which must be optimised for the specific ore.

3.4 Reverse Flotation

Reverse flotation, in which magnesite is selectively floated using sodium oleate (NaOL) as collector while talc is depressed and reports to the cell floor as a non-floating product, consistently achieves the highest magnesite grades reported in the literature. Li et al. (2021) conducted a systematic comparison of five inorganic regulators — sodium hexametaphosphate (SHMP), sodium silicate, trisodium phosphate, tannic acid, and monoammonium oxalate — in a three-stage cationic reverse flotation circuit at pH 5, using cetyltrimethylammonium bromide (CTAB) as collector. SHMP was found to achieve the highest MgO grade in the final concentrate and the highest degree of talc and silicate gangue depression, attributed to its polyphosphate anions forming strong surface complexes with Mg^{2+} sites on gangue mineral surfaces at acidic pH while leaving magnesite surfaces comparatively unaffected. Multi-stage processing is necessary to achieve premium refractory-grade specifications (>47% MgO, <2% SiO2).

3.5 Gravity Separation

Gravity separation exploits the density contrast between talc (2.58–2.83 g/cm³) and magnesite (2.98–3.10 g/cm³). Shaking tables, spirals, and jigging can achieve meaningful pre-concentration of coarser ore fractions. Hojamberdiev et al. (2010) reported that for the Zinelbulak deposit, gravity separation was effective for producing a coarse-grained talc product suitable for certain refractory applications. The principal limitation is particle size: below approximately 50–74 µm, hydrodynamic drag forces dominate over gravitational settling, and separation efficiency falls sharply. Gravity separation is therefore best applied as a pre-concentration or classification step preceding flotation, rather than as a standalone separation method.

3.6 Electrostatic (Triboelectric) Separation

Triboelectric belt separation exploits the surface charge difference generated when talc and magnesite particles contact a belt surface, causing them to acquire opposite charges and separate under an applied electric field. Research from Montanuniversitaet Leoben (2022) compared triboelectric and flotation performance on mineral mixtures containing talc, quartz, dolomite, and magnesite. The key advantage of this dry process is the complete elimination of water and flotation reagents. However, reported talc purity is consistently lower than achievable by flotation, and performance degrades significantly at relative humidity above approximately 60–

65%, limiting applicability in humid climates or without prior feed drying. The effective particle size range is approximately 50–500 µm.

3.7 Comparative Overview

Table 3 summarises the comparative performance characteristics of the five separation methods reviewed. The data represent typical ranges reported for well-liberated feeds under laboratory-scale optimised conditions; industrial performance may differ depending on ore texture, scale, and circuit design.

Table 3. Comparative overview of separation technologies for talc-magnesite ore systems.

Sources: Nanthakumar et al. (2018); Ahmed et al. (2016); Hojamberdiev et al. (2010); Brezani & Zelenak (2013); Montanuniversitaet Leoben (2022). Grade and recovery ranges represent performance.

Method	Operating principle	Talc grade (%)	Talc recovery (%)	Key advantage	Key limitation
Collectorless flotation	Natural hydrophobicity contrast (~76° vs ~43°)	85–92	72–82	No collector; low cost	Fine particle entrainment <40 µm
Direct flotation	SDS/MIBC selective collector for talc	88–93	80–90	High recovery; robust process	pH and dosage sensitive; reagent cost
Reverse flotation	NaOL collects magnesite; talc depressed to cell floor	—	—	Highest MgO grade achievable	Multi-stage required; reagent-intensive
Gravity separation	Density contrast (talc 2.7 vs magnesite 3.0 g/cm3)	75–82	68–75	No reagents; simple operation	Ineffective below ~74 µm
Triboelectric separation	Tribostatic charge difference on belt surface	72–80	65–75	Dry process; zero water use	Humidity sensitive; lower purity than flotation

3.8 Reagent Chemistry and Depressant Systems

Selective depression of talc in reverse flotation — or of magnesite in direct flotation — is the central reagent chemistry challenge in talc-magnesite separation. Depressants function by adsorbing onto the target mineral surface and rendering it hydrophilic, thereby preventing bubble attachment.

Among inorganic depressants, SHMP consistently outperforms sodium silicate in comparative studies, attributed to its stronger and more selective interaction with Mg^{2+} surface sites on silicate gangue minerals at acidic pH (Li et al., 2021). Sodium silicate remains widely used due to its low cost and availability, despite lower selectivity.

Polysaccharide-based organic depressants offer superior selectivity and environmental performance. Carboxymethyl cellulose (CMC) adsorbs strongly on talc edge faces through hydrogen bonding via its hydroxyl and carboxyl groups, with Mg^{2+} ions released during grinding providing activated surface sites that enhance adsorption (Xue et al., 2023). Guar gum operates through a similar galactomannan backbone mechanism (Zhang et al., 2024). Carrageenan has been demonstrated to selectively depress talc in mixed-mineral flotation systems, with depression efficiency increasing progressively with dosage up to approximately 150 mg/L (Zhao et al., 2024). All three polysaccharide depressants maintain high magnesite (or target mineral) recovery even at their effective talc-depressing dosages, confirming selectivity of the mechanism.

Novel chelating agents represent an emerging direction. Glutamic acid diacetic acid tetrasodium salt (GLDA), a biodegradable chelating reagent, was demonstrated by Mao et al. (2024) to selectively interact with Ca^{2+} sites on calcite surfaces via chemisorption, achieving high-grade magnesite in NaOL flotation systems containing talc, magnesite, and calcite. The Ca^{2+}-selective mechanism is relevant to talc-magnesite-calcite ores where conventional depressants lack sufficient three-mineral selectivity. Potassium cetyl phosphate (PCP), a novel phosphate-head collector, was shown by Tang et al. (2020) to achieve high magnesite-dolomite separation selectivity via chemisorption on Mg^{2+} surface sites; its application to talc-magnesite systems represents a logical extension.

3.9 Process Circuit Design Considerations

Practical talc-magnesite separation circuits must be designed with reference to the specific deposit mineralogy, target product specifications, and economic constraints. No universal flowsheet exists. For ores with a wide liberation size range, a combined circuit — gravity or classification-based pre-concentration of the coarse fraction, followed by flotation of the fine fraction — is generally more efficient than a single-method approach applied across all size fractions.

For magnesite-focused circuits targeting refractory-grade product (>46% MgO, <2% SiO2), multi-stage reverse flotation with SHMP as regulator at acidic pH is the best-documented approach in the literature (Li et al., 2021). For talc-focused circuits targeting high-purity cosmetic or ceramic talc (>95% talc), direct flotation at pH 6–7 with SDS combined with a polysaccharide depressant for the fine fraction offers the most selective reported performance (Ahmed et al., 2016; Xue et al., 2023).

A dual-product circuit — recovering both a talc concentrate from the flotation tailings and a magnesite concentrate from the flotation product of a reverse flotation circuit — is economically attractive when both minerals have market value, as is typically the case for Zinelbulak-type ores. Circuit water chemistry management is a critical operational consideration: dissolved Mg^{2+} ions accumulate in recirculated process water and alter the adsorption behaviour of polysaccharide depressants, increasing reagent demand over time.

4. Challenges and Research Gaps

Several persistent challenges limit the efficiency of talc-magnesite separation at both laboratory and industrial scale.

Fine-particle entrainment is the most universally cited limitation in flotation-based separation. Particles below approximately 20–40 µm are recovered mechanically with the froth water regardless of their surface hydrophobicity, reducing concentrate grade and separation selectivity. This problem is particularly acute in ores requiring fine grinding for adequate liberation. Column flotation with froth washing and desliming cyclones offer partial mitigation but add capital and operating cost.

Reagent selectivity decreases as ore complexity increases. In ores containing talc, magnesite, dolomite, and chlorite simultaneously, no currently available single-reagent system achieves complete selectivity among all four phases. Dolomite in particular is difficult to distinguish from magnesite under typical reverse flotation conditions. Combined or sequential reagent systems — for example, SHMP as a pre-treatment followed by NaOL collection — improve selectivity but require careful pH and dosage optimisation for each ore type.

Process water chemistry is an underappreciated operational variable. Dissolved Mg^{2+} ions, released continuously during grinding and flotation of both talc and magnesite, accumulate in recirculated water. At elevated Mg^{2+} concentrations, the adsorption behaviour and dosage requirements of CMC and other polysaccharide depressants change significantly (Xue et al., 2023), destabilising optimised flotation conditions. Regular water chemistry monitoring and controlled bleed or partial softening of process water are necessary in closed-circuit operations.

For triboelectric separation, humidity sensitivity remains an unresolved scale-up barrier. Moisture films on particle surfaces disrupt the tribocharging mechanism, and performance degrades sharply above approximately 60–65% relative humidity (Montanuniversitaet Leoben, 2022). Pre-drying of feed is an energy-intensive countermeasure. Industrial-scale deployment of triboelectric technology for talc-magnesite ores remains limited.

Finally, the lack of standardised experimental reporting in the published literature makes direct comparison of results across studies difficult. Key variables including grind size distribution, pulp density, slurry pH, reagent conditioning sequence, flotation cell design, and ore mineralogy are frequently incompletely reported, limiting the transferability of laboratory findings.

5. Future Research Directions

Table 4 presents a structured research agenda for the field, mapping emerging approaches to performance targets and current technology readiness levels (TRL) based on the authors' assessment of the published literature.

Research direction	Target performance indicator	Current TRL*	Target TRL (5 yr)	Key knowledge gap
ML-assisted flotation control	Grade stability ±1%; reduced reagent variance	3–4	6–7	Multi-variable real-time sensor fusion; labelled training datasets for talc-Mg systems
DFT/MD-guided	Selectivity coefficient >10	3	5	Force field parameterisation

reagent design	for target mineral pair			for Mg-carbonate / phyllosilicate mineral interfaces
Bio-reagent optimisation (EPS)	CMC-equivalent talc depression at <20 mg/L; biodegradable	2–3	5	EPS structure-activity relationships; production scale-up economics
Bifunctional hydrophobic-ionic reagent	Single molecule: talc depression + Mg^{2+} activation	2	4	Bifunctional molecule synthesis; selectivity vs. chain length and head group
Dry electrostatic scale-up	Pilot-scale (>5 t/h); RH tolerance to 70%	3–4	6	Continuous tribocharging; particle size distribution control; electrode geometry
LCA/TEA of integrated circuits	<15 kg CO2/t product; water use <1,000 L/t	—	—	Reagent lifecycle inventory; process simulation; regional water availability

anced talc-magnesite separation — methods, targets, and estimated TRL.

** TRL = Technology Readiness Level (1 = basic principles observed; 9 = proven industrial system). Values represent authors' assessment based on published literature, not a cited external source. EPS = exopolysaccharides. DFT = density functional theory. ML = machine learning.*

6. Conclusions

This review has systematically examined separation technologies for talc-magnesite ore systems based on peer-reviewed literature. The following conclusions are drawn:

(1) The contact angle contrast between talc basal faces (72–79°) and magnesite (40–47°) — confirmed across multiple independent studies — provides the physicochemical basis for flotation-based separation. However, selectivity is strongly particle-size dependent, deteriorating sharply below approximately 40 µm due to mechanical entrainment. Optimal grind size for most deposits is in the range d80 = 74–100 µm.

(2) Collectorless flotation is the simplest and lowest-cost approach but achieves only moderate concentrate purity. Direct flotation with SDS at pH 6–7 offers the highest single-stage talc recovery. Reverse flotation with NaOL and SHMP as regulator at pH 5 achieves the highest

magnesite grades reported in the literature and is the preferred route for producing refractory-grade concentrate.

(3) Among inorganic depressants, SHMP consistently outperforms sodium silicate and phosphate-based alternatives in comparative studies. Among polysaccharide depressants, CMC demonstrates the strongest and most selective talc depression, followed by guar gum and carrageenan, with adsorption proceeding primarily through hydrogen bonding on talc edge faces activated by surface Mg^{2+} sites.

(4) Gravity separation is limited to coarser fractions (>74 μm) and is best used as a pre-concentration or classification step. Triboelectric belt separation eliminates water use entirely but achieves lower purity than flotation and is sensitive to humidity, limiting its current applicability.

(5) Persistent challenges — fine-particle entrainment, multi-mineral reagent selectivity, and process water Mg^{2+} accumulation — remain incompletely solved and constitute priority targets for future research.

(6) Machine learning-assisted process control, bio-based depressant development, bifunctional reagent molecular design, and dry electrostatic scale-up are identified as the most promising near-to-medium-term research directions, currently at TRL 2–4 with realistic targets of TRL 5–7 within five years.

References

1. Brezani, I., Zelenak, S. (2013). Collectorless flotation of talc-magnesite ore with respect to particle size. Acta Montanistica Slovaca, 18(1), 18-25.
2. Hojamberdiev, M., Ryu, G., Yarbayev, A., Yusupov, T., Lee, W.H. (2010). Characterization and processing of talc-magnesite from the Zinelbulak deposit. International Journal of Minerals, Metallurgy and Materials, 17(4), 414-420. DOI: 10.1007/s12613-011-0408-y
3. Nanthakumar, B., Kasthuriarachy, N., Laskowski, J.S. (2018). A review of flotation separation of Mg carbonates (dolomite and magnesite). Minerals, 8(8), 354. DOI: 10.3390/min8080354
4. Ahmed, M.M., Ibrahim, G.A., Hassan, M.H.A. (2016). The art of talc flotation for different industrial applications. International Journal of Mining Engineering and Mineral Processing, 5(2), 32-50.
5. Li, X., Liu, W., Wang, J., Song, S. (2021). Study on regulators of purifying magnesite ore by cationic reverse flotation. Scientific Reports, 11, 16771. DOI: 10.1038/s41598-021-96094-4
6. Xue, J., Tu, H., Shi, J., et al. (2023). Enhanced inhibition of talc flotation using acidified sodium silicate and sodium carboxymethyl cellulose as the combined inhibitor. International Journal of Minerals, Metallurgy and Materials, 30, 1310-1319.
7. Tang, Y., Yin, W.Z., Kelebek, S. (2020). Magnesite-dolomite separation using potassium cetyl phosphate as a novel flotation collector. Applied Surface Science, 508, 145191.
8. Mao, Y., Liu, W., Liu, W., Shen, Y., Zhao, Q. (2024). An environmentally friendly depressant for magnesite and calcite flotation separation. Journal of Environmental Chemical Engineering. DOI: 10.1016/j.jece.2024.113726
9. Sun, Z., Chen, Q., Zhang, Y., et al. (2024). Flotation separation of magnesite from dolomite with gellan gum as depressant. Minerals Engineering, 202, 108281.
10. Zhao, L., Qin, Y., Wang, X., et al. (2024). Flotation separation of molybdenite from talc using carrageenan as depressant. Minerals Engineering, 207, 108551.
11. Zhang, H., Liu, C., Li, F., et al. (2024). Research progress of application and interaction mechanism of polymers in mineral flotation: A review. Polymers, 16(23), 3363. DOI: 10.3390/polym16233363

12. Montanuniversitaet Leoben. (2022). Applicability of electrostatic separation on talc-containing mineral samples vs. flotation. BHM Berg- und Huettenmaennische Monatshefte. DOI: 10.1007/s00501-022-01258-8
13. Fuerstenau, D.W., Diao, J., Williams, M.C. (1988). Characterization of the surface charge of talc. Colloids and Surfaces, 33(1-2), 13-25.
14. USGS. (2023). Mineral Commodity Summaries: Magnesium Compounds. U.S. Geological Survey, Reston, VA.
15. Sheng, Q., Yin, W., Zhang, Y., Hawboldt, K. (2023). Selective depression of talc in cuprite sulfidization flotation by new depressant astragaloside. Proceedings COM 2022, Springer.
16. Yehia, A., Al-Wakeel, M.I. (2000). Talc separation from talc-carbonate ore to be suitable for different industrial applications. Minerals Engineering, 13(1), 111-116.

1.